

## Material Spec sheet

### EPDM 70-AQE12889

TEST	TEST METHOD	RESULT
Hardness (IRHD)	ISO 48	70 +/- 5
SG	ISO 1183	1.35
Tensile Strength (Mpa)	ISO 37	10.25 Mpa
Elongation @ Break (%)	ISO 37	335.7 %
<u>Compression Set (%)</u> 24hrs @ 70c	ISO 815	17.90 %
Ozone/Weathering		Excellent
Operating temperature range		-25 to +110C

The above material has been developed to withstand salt water environments & impacts. While we advise the above figures we can't be held responsible for any damages or faults to the rubber or other items relating to the use of the rubber products manufactured.

We can supply a test cert for every batch if requested on the purchase order this is given as a guide only.

EPDM-E12889-BRL-14102016-Rev1